

TL-81GF

Glass Flake Filled Epoxy Lining

PRODUCT DESCRIPTION

Blome TL-81GF is a 100% solids, glass flake filled Epoxy product for steel and concrete tank lining applications. It can be applied at thickness ranging from 15 mils to 50 mils in single or multiple coats. TL-81GF is also suited for coating structural steel and concrete in harsh fume or vapor service. Blome TL-81GF has excellent resistance to splash & spills of many corrosive chemicals.

TL-81GF is a two-component product with a 4:1 volumetric mix ratio. It is typically applied by plural component spray equipment, brush, roller, or trowel at thickness of 15 to 50 mils, in one or two coats. TL-81GF offers excellent resistance to many harsh chemicals including dilute mineral acids, concentrated alkalis, fuels, oils, salts and many solvents. TL-81GF offers high impact resistance, resistance to cracking when exposed to high temperatures or thermal shock, excellent edge coat properties, excellent bond strength to steel and good surface tolerance.

GENERAL USES

TL-81GF is suitable for a variety of lining applications including:

- Linings for FGD system tanks
- Acid Storage Tanks (interior and exterior)
- Chemical Storage Tanks
- Fuel and Oil Storage Tanks

HANDLING CHARACTERISTICS

TL-81GF may be applied using a spray rig as directed by the manufacturer. Blome International recommends using a plural component spray rig equipped with a 4:1 volumetric ratio apparatus. TL-81GF may be applied using brush or rollers. Application thickness will vary dependant upon service conditions. Consult Blome Tank Lining Systems Guide or Blome Tech Service for specific recommendations.

TYPICAL PROPERTIES-WET

Solids by Volume:	100%
Weight per Mixed Gallon:	9.5
Pot-life: 55°F:	40-50 min
75°F:	20-25 min
Cure Time (approximate): Dry To Touch: 55°F:	8 hrs
75°F:	5 hrs
Firm: 55°F:	24 hrs
75°F:	12 hrs
Chemical Service: 55°F:	72 hrs
75°F:	36 hrs
Primer:	Concrete: Primer 75
	Steel: optional
Flammability:	Nonflammable

TYPICAL PROPERTIES –CURED

Color:	Gray & Red
Hardness –ASTM D-2240 Shore D:	73
Compressive Strength -ASTM C-579:	12,400 psi
Tensile Strength –ASTM D-638:	7,000 psi
Flexural Strength –ASTM D-790:	9,300 psi
Permeability:	0.002 perm. – in.
Bond Strength –ASTM D-4541: Concrete:	Failure In Concrete
Steel:	1500 psi

PACKAGING & STORAGE

TL-81GF is packaged in 1-gallon, 5-gallon, and 25-gallon units. Each unit consists of a premeasured Part A and Part B components.

Keep TL-81GF tightly sealed in original containers until ready for use. Store at 50°F to 75°F, out of direct sunlight. Properly stored, TL-81GF products have a minimum shelf life of one year. Refer to lot number printed on label for date of manufacture.

BID SPECIFICATION GUIDE

Use TL-81GF 100% solids, cycloaliphatic amine cured, Epoxy tank lining system as manufactured by Blome International, O'Fallon MO.

APPLICATION GUIDELINES**ENVIRONMENTAL
CONDITIONS**

Weather conditions, especially dew point, should be constantly monitored during the work being done. Final blast cleaning and application of tank lining system must only be performed when the temperature of the steel substrate will not fall within 5°F of the dew point. Dehumidification and/or temperature control may be necessary to meet this requirement. Use a surface thermometer to frequently monitor the temperature of the steel substrate before and during application.

**JOBSITE STORAGE OF
MATERIALS**

Proper storage of Blome International products is important to a successful application. Store components (Part A and Part B) unopened, in a dry place, at 50°F to 75°F, out of direct sunlight, and protected from the elements. Keep away from heat and flame. For the 24 to 36 hours just prior to use adjust the storage temperature to 75°F to 85°F to facilitate handling.

SURFACE PREPARATION

Immediately prior to application of the product:

The steel substrate must be clean of all oil, grease, dirt, dust, mill scale, rust, flash rust, corrosion product, salts, solvents, chlorides, other chemicals, and existing coatings. All welds must be smooth and continuous. All weld splatter, buckshot, laminations, and slivers must be removed and ground smooth; undercuts and pinholes must be ground smooth and filled with weld metal. All projections, high points, sharp edges, and fillets must be ground smooth to a radius of at least 1/8 inch and all corners must be rounded. All pitting, scratches, gouges, and other defects must be repaired either by welding or by filling with Blome 83MP repair materials that are compatible with TL-81GF and suitable for the intended service conditions. All surfaces to be coated or lined must be readily accessible. For tank linings, the steel must be blasted to a White Metal Finish (NACE No. 1, SSPC SP 5) with a 2 to 4 mil dense, sharp anchor profile. For exterior coatings, the steel must be blasted to a Near White Metal Finish (NACE No.2, SSPC SP 10) with a 2 to 3 mil dense, sharp anchor profile.

MASKING & PROTECTION

Mask or remove adjacent surfaces and equipment that are not to be lined. Protect nearby equipment from spent abrasive exiting the tank while blasting.

APPLICATION EQUIPMENT

TL-81GF may be applied using a spray rig, notched trowel, brush or roller.

Spraying TL-81GF:

1. Use a plural component airless spray rig with a fixed ratio of 4:1 such as a Graco "King" Hydro-Cat or equal.

2. Always use spray equipment in accordance with equipment manufacturer's instructions.
3. Care of Spray Rig Hoses:
Take care to prevent the mixed material from setting up in your hoses. Keep hoses as short as possible, purge them immediately if work is interrupted, keep them out of direct sunlight and insulated, or away from hot surfaces.

The mix ratio of Part A to Part B is 4:1 A to B by volume.

MIXING TECHNIQUE

Use a Jiffy type mixer for all mixing. When operating the mixer avoid plunging it up and down in the bucket. This will fold air into the resin, causing bubbles to form after the coating has been applied.

WORKING TIME

The working time for mixed material is short. If work is delayed, even momentarily, immediately flush the whip hose and gun.

The warmer the components are when mixed, the shorter the working time will be. But, materials should be at least 90°F to spray properly. If possible, shade the spray rig.

Keep hoses as short as possible. Keep hoses out of direct sunlight and insulated, or away from hot surfaces. Purge hoses immediately if work is interrupted.

Stripe all welds and edges with a brush coat to assure adequate protection of these areas.

All spot welds should be puttied before applying final coats. Refer to project specifications and/or Blome International for putty material recommendations.

Use a wet mil thickness gauge and frequently monitor lining thickness.

MIXING & APPLICATION

1. Individually stir Part A and Part B components to a smooth, uniform consistency and color. Any settling in the containers must be thoroughly scraped up and remixed prior to mixing or application.
2. If using a plural component spray rig, skip this step.
Pour the entire contents of Part B into the container holding the Part A, and mix thoroughly for 2 minutes. The pot life of the mixture will be approximately 20 to 25 minutes at 75°F (Significantly less at higher temperatures). The longer the material is in the bucket after mixing, the shorter its pot life will be. Use it immediately once mixed.
3. If applying with a plural component spray rig:
Pour the pre-mixed Part A and Part B components into their respective hoppers on the rig. Circulate the separate components through their hoses until both reach the correct working temperature. Part A should be at 100°F, and Part B should be at 90°F.
4. Apply the TL-81GF at the specified mil thickness and allow to cure.

Note: Post curing may be desirable in certain circumstances. Check with Blome International.

TOUCH UP OR RE-COATING

Before any touch-up or re-coat material can be applied, the first coat must be properly prepared for maximum inter coat adhesion.

- 1) The first coat must be cured firm to the touch, clean, dry and free of blush or surface contaminants.
- 2) If the lining materials to be recoated has cured beyond 24-hours or has been in direct sunlight for more than 12 hours, the surface must be cleaned and abraded to remove gloss prior to application of the recoat material.

CLEAN UP

The following tips will be helpful in cleaning hand tools and equipment after use:

Before TL-81GF gels, it can be cleaned from hand tools and equipment using hot, soapy water.

Spray equipment should be cleaned and flushed with solvents before coating material begins to gel.

Follow equipment manufacturer's recommendations for proper cleaning and care instructions.

After TL-81GF gels, solvents will be required for cleaning. Chlorinated solvents may be used if flammable solvents are prohibited.

CAUTION

TL-81GF may cause skin irritation with prolonged or repeated contact. Handle with care and read the material safety data sheet, which is available for each product.

WARRANTY

We warrant that our goods will conform to the description contained in the order and that we have good title to all goods sold. Our material data sheets and other literature are to be considered accurate and reliable, but are used as guides only. WE GIVE NO WARRANTY OR GUARANTEE, WHETHER OF MERCHANTABILITY OR FITNESS OF PURPOSE OR OTHERWISE, AND WE ASSUME NO LIABILITY IN CONNECTION THEREWITH. We are happy to give suggestions for applications; however, the user assumes all risks and liabilities in connection therewith regardless of any suggestion, we may give. We assume no liability for consequential or incidental damages. Our liability, in law and equity, shall be expressly limited to the replacement of non-conforming goods at our factory, or at our sole option, to repayment of the purchase price of the non-conforming goods.

Printed: July 15, 2012
Supersedes all previous literature