

CP-110 HB **High Bond Vinyl Ester Mortar**

PRODUCT DESCRIPTION

Blome CP-110 HB is a two-component, silica filled vinyl ester mortar used for the installation of chemical resistant brick and tile. CP-110 HB is designed for bonding acid brick and tile in tank, floor and trench applications requiring resistance to acids, bleaches, alkalis, solvents and other corrosive chemicals. CP-110 is especially suited for use in applications requiring resistance to strong oxidizers such as chlorine, chlorine dioxide, hypochlorite bleaches and oxidizing acids such as nitric and chromic. This product also has excellent resistance to phosphoric and hydrochloric acid. The material exhibits excellent bond strength to acid brick and tile and is well suited for applications requiring high physical properties. CP-110 HB can also be used to repair bugholes and other surface imperfections in concrete prior to the application of Blome vinyl ester environmental (EC) and tank (TL) lining products.

CP-110 HB is supplied as a two-component mortar with improved shelf life on both Powder and Resin components. When properly stored, CP-110 HB components have up to nine (9) months shelf life. In some instances, small amounts of accelerator may be needed to “refresh” pails of older resin. Consult Blome for mixing details.

TYPICAL USES

Blome CP-110 HB is suitable for bonding chemically resistant brick and tile in a variety of applications including:

- Bleach Towers and Process Vessels
- Acid brick and tile flooring and trenches
- Repair material for concrete prior to application of Blome environmental coatings and tank linings

HANDLING CHARACTERISTICS

Blome CP-110 HB offers preferred trowelling & handling properties with sufficient thixotropy for successful installation of glazed tile. CP-110 HB is smooth spreading and will support a ¼” mortar joint on vertical installations. CP-110 HB will hold brick and tile and secure them from slipping while the mortar cures. CP-110 HB cures rapidly and provides an excellent bond to acid brick and glazed tile. This unique material produces quality results and high production rates.

TYPICAL PROPERTIES **WET**

Components:	Two (2) - powder & resin
Wet mortar density:	120-123 lbs./ft ³
Mixed consistency:	Creamy mortar
Pot life:	50°F - 45-50 minutes 77°F - 25-30 minutes
Initial set:	50°F - 8 – 10 hours 77°F - 2 – 4 hours
Final cure:	50°F - 9 days minimum 77°F - 7 days minimum

CURED

Blome CP-110 HB complies with ASTM C-395	
Absorption (ASTM C-413)	Less than 0.4%
Bond Strength to brick	Blome test - brick failure
Thermal Expansion Coefficient (ASTM C-531)	12×10^{-6} in/in/°F
Color	Off white
Compressive Strength (ASTM C-579)	12,500 psi
Temperature limit	Continuous: 210°F In suitable chemical service Excursions: 250°F vapor 350°F dry
Tensile Strength (ASTM C-307)	2,400 psi

PACKAGING & STORAGE

Blome CP-110 HB is supplied as a two-component product, with a filler powder and a resin. CP-110 HB Powder (Part A) is packaged in 35 lb. Bags and CP-110 HB Resin (Part B) is packaged in 40 lb. pails or 450 lb. Drums. Use a mix ratio of 3.5 pbw to 1.0 pbw for acid brick installations requiring tighter joints or for tuck pointing. CP-110 HB may be mixed up to 4.0 pbw to 1.0 pbw Powder to Resin for installing heavy glazed tile.

Unit Size	180 lbs. (~1.5 cubic feet)
Powder	140 lbs. (4 x 35 lb. bags)
Resin	40 lbs. (1 x 40 lb. pails)

Shelf life for CP-110 HB components is up to nine (9) months if stored below 70°F at 50% relative humidity. Keep CP-110 HB components tightly sealed in original containers until ready for use. Store components in a cool, dry place, out of direct sunlight on pallets, between 50°F - 80°F. For maximum shelf life, protect bags of Powder from water, humidity and weather, and keep Resin out of direct sunlight while in storage and on job site.

ESTIMATED COVERAGE

Please refer to Blome Brick Mortar Usage Chart in Chemical Proofing Section of Blome Catalog. This chart has estimated usage rates and does not allow for waste, joint variations or other variables.

BID SPECIFICATION GUIDE

Use Blome CP-110 HB High Bond Vinyl Ester Mortar as produced by Blome International, O'Fallon, MO.

JOB SITE ENVIRONMENTAL CONDITIONS

Blome CP-110 HB must be applied while ambient temperatures are between 50°F and 90°F. Blome CP-110 HB components, brick, tile and substrate temperatures must also be maintained in this range. Blome Vinyl Ester Low Temperature Accelerator is available for use when temperatures drop below 50° F. Consult Blome for application and use details. Installations of CP-110 HB should be protected from water and weather during installation and curing.

SURFACE PREPARATION

Brick or tile to be installed with Blome CP-110 HB must be clean, dry and oil free. If brick or tiles have been frozen, they must be thawed completely and allowed to dry prior to installation with Blome CP-110 HB. If applied over Liquid or Sheet membranes, these surfaces should be clean and dry prior to installation of Blome CP-110 HB bed joint. These surfaces should be swept clean and be free of dirt, dust, water or other job site contaminants.

SAFETY PRECAUTIONS

Blome CP-110 HB Powder, Resin and mixes of them present various health hazards if handled improperly. Refer to Material Safety Data Sheet before working with this product. CP-110 HB Powder contains silica and peroxide powders and CP-110 HB Resin is flammable and will cause eye injury and irritate skin. Wear respirator suitable for silica and peroxide powders, safety glasses with side shields, gloves and long sleeve shirts to prevent all contact with skin and eyes. After working with Blome CP-110 HB, wash thoroughly before eating, drinking, smoking or other activities.

APPLICATION EQUIPMENT

Blome CP-110 HB is best mixed with a KOL, pail type mixer or in a pail using a drill motor driven paddle blade. This mixing equipment must be clean, dry and free of any contaminants including Portland cement, other mortars or resins. When mixed, CP-110 HB is applied to tile or brick with a pointing or margin trowel. **Application and mixing equipment need not be spark proof/explosion proof when mixing or handling the mixed mortar.**

MIXING AND APPLICATION

Add approximately 3.5 parts by weight CP-110 HB Powder to 1.0 part by weight CP-110 HB Resin (up to 4 parts may be used if a very stiff mix is required for large, heavy tiles). Mix components using a clean, dry mechanical mixer or trowel for a minimum of 2-3 minutes, making sure there are no lumps or dry pockets of powder. The amount of powder may be adjusted, up or down, to achieve desired consistency for specific uses. More powder will produce a thicker consistency for vertical or overhead applications. Using a clean, dry pointing or margin trowel, butter tile evenly on 2 or 3 sides. Slide buttered tile into place, squeezing excess mortar from joints and striking off. Mortar joint thickness should be 1/8" to 1/4".

CLEANUP

All tools, mixing equipment, gloves and application equipment should be cleaned up immediately using a citrus or biodegradable cleanser, with hot water, while material is still wet. If material begins to cure, solvent-based cleaners will be required for removal.

WARRANTY

We warrant that our goods will conform to the description contained in the order and that we have good title to all goods sold. Our material data sheets and other literature are to be considered accurate and reliable, but are used as guides only. WE GIVE NO WARRANTY OR GUARANTEE, WHETHER OF MERCHANT ABILITY OR FITNESS OF PURPOSE OR OTHERWISE, AND WE ASSUME NO LIABILITY IN CONNECTION THEREWITH. We are happy to give suggestions for applications; however, the user assumes all risks and liabilities in connection therewith regardless of any suggestion, we may give. We assume no liability for consequential or incidental damages. Our liability, in law and equity, shall be expressly limited to the replacement of non-conforming goods at our factory, or at our sole option, to repayment of the purchase price of the non-conforming goods.

Revised: May 3, 2016
Supersedes all previous literature